



The product can be pigmented.

TECHNICAL CHART 74

# PURE VARNISH BICO MATT 05

## Description of product

Water-based polyurethane two-component matt varnish, with an excellent transparency.

## Application field

Protective finishing for walls and floors, exposed to high degree of humidity.

## Product characteristics

PURE VARNISH BICO MATT 05 protects the treated surfaces forming a uniform matt waterproof film, which has the following characteristics:

- excellent adherence to the major part of surfaces, if dry and properly treated;
- great resistance to usury;
- great flexibility.

Technical data	
Name	Pure Varnish Bico Matt 05
Composition	Water-based matt resin for walls and floors
Aspect	Milky liquid
Color	Transparent
Catalysis	20% of CTW 78 hardener (catalyze before any dilution in water)
Dilution	Ready to use (eventual dilution in water 10-25%)
Quantity per layer	approx. 7 - 10 m <sup>2</sup> /l
VOC class	VOC 0 g/l, wall paint and subcategory "L" max.value UE2010 30g/l
Specific weight	1,05 g/cm <sup>3</sup>
Packaging	1 - 5 liters packages
Storage	The product remains unchanged for at least one year if kept in a closed and sheltered environment at a temperature between 5 - 35 °C. Protect from frost!
Notice	<ul style="list-style-type: none"> <li>• Add the catalyst under stirring and allow to rest for at least 5 minutes.</li> <li>• Avoid using preheaters.</li> <li>• Mix the product well before use.</li> <li>• Use the mixed product within 3 hours.</li> <li>• Do not dispose of paint residues in the sewers.</li> <li>• The equipment should be washed immediately after use with water.</li> </ul>

## **PURE VARNISH BICO MATT 05**

---

### **Instructions for use**

- Pour CTW 78 into PURE VARNISH BICO MATT 05 and mix thoroughly.
- Application with roller or spray.
- The product is applied in 2 or more coats.
- Apply the next coat after the hardening of the previous one.
- Do not apply below 15 °C.

### **Note**

The present technical chart has been written by Bericalce's experts and the indicated technical and scientific information have been tested in our own workshop.

Any responsibility regarding the results are due only to the method and conditions used during application of the product.

These indications are a valid support for testing the quality of the product in each specific case.

**Date of issue 01.09.2017**

### **BeriCalce ITALIA**

Via Odorico da Pordenone, 18

36100 Vicenza - ITALIA

Tel./Fax (+39) 0444 929102

Tel. (+39) 0444 923317

Skype: bericalce

info@bericalce.com

**bericalce.com**